



## C-BX 0900

Fiber Type: Carbon  
 Architecture: +45°/-45° Double Bias  
 Dry Thickness: 0.018 in. / 0.46 mm  
 Total Weight: 8.73 oz/sq.yd / 296 g/sq.m

**VECTORULTRA™**



Roll Specifications			Fiber Architecture Data	
Roll Width:	Roll Weight:	Roll Length:	0 ° :	n/a
50 in / 1270 mm	88 lb / 40 kg	113 yd / 103 m	45 ° :	4.37 oz/sq.yd / 148 g/sq.m
			90 ° :	n/a
			- 45 ° :	4.37 oz/sq.yd / 148 g/sq.m
			Chopped Mat :	n/a

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

### Laminated Properties

45 °

45 °

Laminate Weight		
(lb/sq.ft)	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
Fiber	0.06	0.06
Resin	0.03	0.07
Total	0.09	0.13

Physical Properties		
	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
Density (g/cc)	1.53	1.41
Fiber Content (% by Wt.)	65%	45%
Thickness (in)	0.012	0.018

Laminate Moduli		
(MSI)	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
Ex	8.52	5.69
Ey	8.52	5.69
Gxy	0.37	0.25
Ex,flex.	8.09	5.40
Ey,flex.	8.09	5.40

Ultimate Stress		
(KSI)	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
Long. Ten.	81	54
Long. Comp.	74	50
Trans. Ten.	81	54
Trans. Comp.	74	50
In-Plane Shear	7	5
Long. Flex.	83	55
Trans. Flex.	83	55

In-Plane Stiffness, "EA"		
10 <sup>^3</sup> lb/in	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
(EA)x	100	104
(EA)y	100	104
(GA)xy	4	5

Ultimate In-Plane Load		
lb/in	C-BX 0900 Resin Infused	C-BX 0900 Open Mold
Long. Ten.	947	987
Long. Comp.	875	912
Trans. Ten.	947	987
Trans. Comp.	875	912
In-Plane Shear	88	90

**Notes:**

- 1: Resin infused laminate made with vinyl ester resin 200 cps viscosity @ 77° F.
- 2: Open mold laminate made with polyester resin.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.