



C-L 0900

Fiber Type: Carbon
 Architecture: 0° Unidirectional
 Dry Thickness: 0.013 in. / 0.33 mm
 Total Weight: 8.99 oz/sq.yd / 305 g/sq.m

VECTORULTRA™

Roll Specifications			Fiber Architecture Data	
Roll Width: 24 in / 610 mm	Roll Weight: 74 lb / 34 kg	Roll Length: 200 yd / 183 m	0 ° : 8.99 oz/sq.yd / 305 g/sq.m	
			45 ° : n/a	
			90 ° : n/a	
			- 45 ° : n/a	
			Chopped Mat : n/a	

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

Laminate Weight (lb/sq.ft)		
	C-L 0900 Resin Infused	C-L 0900 Open Mold
Fiber	0.06	0.06
Resin	0.03	0.08
Total	0.10	0.14

Physical Properties

	C-L 0900 Resin Infused	C-L 0900 Open Mold
Density (g/cc)	1.53	1.41
Fiber Content (% by Wt.)	65%	45%
Thickness (in)	0.012	0.019

Laminate Moduli		
(MSI)	C-L 0900 Resin Infused	C-L 0900 Open Mold
Ex	16.81	10.99
Ey	0.61	0.61
Gxy	0.37	0.25
Ex,flex.	15.92	10.39
Ey,flex.	0.58	0.58

Ultimate Stress		
(KSI)	C-L 0900 Resin Infused	C-L 0900 Open Mold
Long. Ten.	202	132
Long. Comp.	129	84
Trans. Ten.	5	5
Trans. Comp.	19	19
In-Plane Shear	8	7
Long. Flex.	129	84
Trans. Flex.	5	5

In-Plane Stiffness, "EA"		
10 ³ lb/in	C-L 0900 Resin Infused	C-L 0900 Open Mold
(EA)x	203	208
(EA)y	7	12
(GA)xy	5	5

Ultimate In-Plane Load		
lb/in	C-L 0900 Resin Infused	C-L 0900 Open Mold
Long. Ten.	2,441	2,492
Long. Comp.	1,560	1,592
Trans. Ten.	61	95
Trans. Comp.	231	362
In-Plane Shear	94	139

Notes:

- 1: Resin infused laminate made with vinyl ester resin 200 cps viscosity @ 77° F.
- 2: Open mold laminate made with polyester resin.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.