



E-3LTi 5400

Fiber Type: E-Glass
 Architecture: 0/90 Biaxial
 Dry Thickness: 0.080 in. / 2.03 mm
 Total Weight: 53.76 oz/sq.yd / 1823 g/sq.m

VECTORFUSION
INFUSION-SPECIFIC REINFORCEMENTS

Roll Specifications

Roll Width: 60 in / 1524 mm
 Roll Weight: 220 lb / 100 kg
 Roll Length: 37 yd / 34 m

Fiber Architecture Data

0 ° : 26.88 oz/sq.yd / 911 g/sq.m
 -45 ° : n/a
 90 ° : 26.88 oz/sq.yd / 911 g/sq.m
 45 ° : n/a
 A-Glass Veil : n/a

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

Laminate Weight

(lb/sq.ft)	E-3LTi 5400 Resin Infused
Fiber	0.37
Resin	0.26
Total	0.63

In-Plane Stiffness, "EA"

10 ³ lb/in	E-3LTi 5400 Resin Infused
(EA) _x	215
(EA) _y	215
(GA) _{xy}	35

Physical Properties	
	E-3LTi 5400 Resin Infused
Density (g/cc)	1.74
Fiber Content (% by Wt.)	59%
Thickness (in)	0.070

Ultimate Stress (KSI)	
	E-3LTi 5400 Resin Infused
Long. Ten.	53
Long. Comp.	45
Trans. Ten.	58
Trans. Comp.	43
In-Plane Shear	7
Long. Flex.	62
Trans. Flex.	62

Notes:

1: Laminate made with poly / vinyl ester resin blend.

Ultimate In-Plane Load lb/in	
	E-3LTi 5400 Resin Infused
Long. Ten.	3,712
Long. Comp.	3,170
Trans. Ten.	4,067
Trans. Comp.	3,003
In-Plane Shear	519

Laminate Moduli (MSI)	
	E-3LTi 5400 Resin Infused
Ex	3.08
Ey	3.08
Gxy	0.51
Ex,flex.	2.92
Ey,flex.	2.92



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

REV: 5/26/2011

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilising a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.