



## E-LT 1800-P

Fiber Type: E-Glass  
 Architecture: 0/90 Biaxial  
 Dry Thickness: 0.022 in. / 0.56 mm  
 Total Weight: 17.92 oz/sq.yd / 608 g/sq.m



### Roll Specifications

Roll Width: 50 in / 1270 mm  
 Roll Weight: 199 lb / 90 kg  
 Roll Length: 122 yd / 112 m

### Fiber Architecture Data

0 ° : 8.96 oz/sq.yd / 304 g/sq.m  
 45 ° : n/a  
 90 ° : 8.96 oz/sq.yd / 304 g/sq.m  
 -45 ° : n/a  
 Chopped Mat : n/a

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

### Laminated Properties

0 °

0 °

#### Laminate Weight

(lb/sq.ft)	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
Fiber	0.12	0.12
Resin	0.05	0.10
Total	0.18	0.23

#### Physical Properties

	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
Density (g/cc)	1.90	1.69
Fiber Content (% by Wt.)	70%	55%
Thickness (in)	0.018	0.026

Laminate Modulii		
(MSI)	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
Ex	3.91	2.82
Ey	3.91	2.82
Gxy	0.66	0.47
Ex,flex.	3.71	2.68
Ey,flex.	3.71	2.68

Ultimate Stress		
(KSI)	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
Long. Ten.	74	53
Long. Comp.	74	53
Trans. Ten.	74	53
Trans. Comp.	74	53
In-Plane Shear	13	9
Long. Flex.	88	64
Trans. Flex.	88	64

In-Plane Stiffness, "EA"		
10 <sup>3</sup> lb/in	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
(EA)x	70	73
(EA)y	70	73
(GA)xy	12	12

Ultimate In-Plane Load		
lb/in	E-LT 1800-P Resin Infused	E-LT 1800-P Open Mold
Long. Ten.	1,330	1,375
Long. Comp.	1,330	1,375
Trans. Ten.	1,330	1,375
Trans. Comp.	1,330	1,375
In-Plane Shear	236	242

**Notes:**

- 1: Resin infused laminate made with a poly / vinyl ester resin blend.
- 2: Open mold laminate made with poly / vinyl ester resin blend.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

REV: 5/3/2011

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilising a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.