



E-LTM 5015

Fiber Type: E-Glass
 Architecture: 0/90 Biaxial
 Dry Thickness: 0.075 in. / 1.91 mm
 Total Weight: 62.62 oz/sq.yd / 2123 g/sq.m

LABORSAVER™



Roll Specifications

Roll Width: 50 in / 1270 mm
 Roll Weight: 200 lb / 91 kg
 Roll Length: 36 yd / 33 m

Fiber Architecture Data

0 ° : 35.68 oz/sq.yd / 1210 g/sq.m
 45 ° : n/a
 90 ° : 13.44 oz/sq.yd / 456 g/sq.m
 -45 ° : n/a
 Chopped Mat : 13.50 oz/sq.yd / 458 g/sq.m

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

Laminate Weight

(lb/sq.ft)	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
Fiber	0.43	0.43
Resin	0.21	0.46
Total	0.64	0.90

Physical Properties

	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
Density (g/cc)	1.86	1.61
Fiber Content (% by Wt.)	68%	49%
Thickness (in)	0.066	0.107

Laminate Modulii		
(MSI)	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
Ex	3.95	2.64
Ey	2.73	1.83
Gxy	0.66	0.45
Ex,flex.	3.75	2.51
Ey,flex.	2.60	1.74

Ultimate Stress		
(KSI)	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
Long. Ten.	65	43
Long. Comp.	75	50
Trans. Ten.	45	30
Trans. Comp.	52	35
In-Plane Shear	15	10
Long. Flex.	89	60
Trans. Flex.	62	41

In-Plane Stiffness, "EA"		
10 ³ lb/in	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
(EA)x	262	282
(EA)y	181	195
(GA)xy	43	48

Ultimate In-Plane Load		
lb/in	E-LTM 5015 Resin Infused	E-LTM 5015 Open Mold
Long. Ten.	4,294	4,624
Long. Comp.	4,957	5,338
Trans. Ten.	2,974	3,203
Trans. Comp.	3,434	3,698
In-Plane Shear	991	1,098

Notes:

- 1: Resin infused laminate made with a poly / vinyl ester resin blend.
- 2: Open mold laminate made with poly / vinyl ester resin blend.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

REV: 5/3/2011

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.