



E-M 0015

Fiber Type: E-Glass
 Architecture: Random
 Dry Thickness: 0.028 in. / 0.71 mm
 Total Weight: 13.50 oz/sq.yd / 458 g/sq.m



| Roll Specifications | | | Fiber Architecture Data | |
|---------------------|----------------|----------------|-------------------------|-----------------------------|
| Roll Width: | Roll Weight: | Roll Length: | 0 ° : | n/a |
| 50 in / 1270 mm | 145 lb / 66 kg | 119 yd / 109 m | 45 ° : | n/a |
| | | | 90 ° : | n/a |
| | | | - 45 ° : | n/a |
| | | | Chopped Mat : | 13.50 oz/sq.yd / 458 g/sq.m |

1: Packaging: box or bag.

2: Weights do not include polyester stitching.

Laminated Properties

0 °

0 °

| Laminate Weight (lb/sq.ft) | E-M 0015 Resin Infused | E-M 0015 Open Mold |
|-------------------------------|---------------------------|-----------------------|
| Fiber | 0.09 | 0.09 |
| Resin | 0.05 | 0.26 |
| Total | 0.14 | 0.36 |

Physical Properties

| | E-M 0015 Resin Infused | E-M 0015 Open Mold |
|--------------------------|---------------------------|-----------------------|
| Density (g/cc) | 1.84 | 1.39 |
| Fiber Content (% by Wt.) | 66% | 26% |
| Thickness (in) | 0.015 | 0.049 |

| Laminate Moduli | | |
|-----------------|---------------------------|-----------------------|
| (MSI) | E-M 0015 Resin Infused | E-M 0015 Open Mold |
| Ex | 1.67 | 0.83 |
| Ey | 1.67 | 0.83 |
| Gxy | 0.62 | 0.30 |
| Ex,flex. | 1.38 | 0.67 |
| Ey,flex. | 1.38 | 0.67 |

| Ultimate Stress | | |
|-----------------|---------------------------|-----------------------|
| (KSI) | E-M 0015 Resin Infused | E-M 0015 Open Mold |
| Long. Ten. | 27 | 14 |
| Long. Comp. | 38 | 19 |
| Trans. Ten. | 27 | 14 |
| Trans. Comp. | 38 | 19 |
| In-Plane Shear | 15 | 10 |
| Long. Flex. | 43 | 21 |
| Trans. Flex. | 43 | 21 |

| In-Plane Stiffness, "EA" | | |
|--------------------------|---------------------------|-----------------------|
| 10 ^{^3} lb/in | E-M 0015 Resin Infused | E-M 0015 Open Mold |
| (EA)x | 25 | 41 |
| (EA)y | 25 | 41 |
| (GA)xy | 9 | 15 |

| Ultimate In-Plane Load | | |
|------------------------|---------------------------|-----------------------|
| lb/in | E-M 0015 Resin Infused | E-M 0015 Open Mold |
| Long. Ten. | 409 | 669 |
| Long. Comp. | 568 | 931 |
| Trans. Ten. | 409 | 669 |
| Trans. Comp. | 568 | 931 |
| In-Plane Shear | 226 | 485 |

Notes:

- 1: Resin infused laminate made with vinyl ester resin 200 cps viscosity @ 77° F.
- 2: Open mold laminate made with polyester resin.
- 3: All standard reinforcements should be infused with a flow aid or Vectorfusion® reinforcements.



3500 Lakewood Dr. Phenix City, AL 36867 tel. 334 291 7704 fax. 334 291 7743

Disclaimer:

As a service to customers, Vectorply Corporation ("VP") may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by VP in combination with other materials or systems.

VP makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by VP. Specifications of reinforcements may change without notice.